





PRODUCT RANGE PROPERTIES

Product	HARDNESS	REDUCTION OF FRICTION	FLEXIBILITY	EASY TO CLEAN
HYPERCOAT V3	XX	XXX	XX	XX
HYPERCOAT DC 86	X	X	XXX	X
HYPERCOAT DC 73	X	X	X	XX
HYPERCOAT DT B30	XX	XX	X	XXX

LEGEND:

X: LOW

XX: MEDIUM

XXX: HIGH

CLEANING OF SURFACE:

If the surface is very dirty, it can be cleaned with a specific product from our range (PURECLEAN) and, before application, dried by Isopropyl Alcohol.

Once the product has been applied, cleaning of the surface will be very simple (Easy to clean) and can be done simply by water or our neutral cleaning product



HYPERCOAT PRODUCT RANGE


	HYPERCOAT V3	HYPERCOAT DC 86	
CHEMICAL NATURE	Silicium compound	Silicium compound	
ACTIVE MATTER	Approx. 30 %	Approx. 20 %	
CARRIER	Solvent	Solvent	
DOSAGE	20-25 g/sqm	25-30 g/sqm	
COATING	HARD	FLEX	
System application	Spray HVLP	Spray HVLP	
CURING	72 h - RT	72 h - RT	





PROPERTIES OF HYPERCOAT RANGE

- Excellent substrate adhesion
- UV and chemical resistant
- High hardness
- Excellent easy-to-clean properties
- Permanent barrier layer
- Good corrosion protection
- No weight impact of treatment
- Very good temperature stability up to 1000 ° C
- Excellent weather resistance





BENEFITS OF HYPERCOAT RANGE

- Friction reduction (up to 7%)
- Turbolence reduction (up to 4%)
- Reduction of coating erosion
- Incresing of resistance from dirt and dust
- Weathering resistance (rain, sun, hail, freezing-thaw, etc.)
- Corrosion resistance from sea salt and water
- Antifreeze, prevent ice sticking
- Increasing of harndess and improving of Impact resistance
- Maintenance cost reduction

